



PLASTOL 3610 N

HIGH RANGE WATER REDUCING ADMIXTURE - RETARDING SUPERPLASTICIZER

EUCLID CHEMICAL
HIGH-RANGE WATER REDUCING ADMIXTURE
PLASTOL 3610 N

Rev:01, 04/20

DESCRIPTION

PLASTOL 3610 N is a polycarboxylate plasticising admixture manufactured with state of the art chemistries developed for the production of high performance concrete / high strength concrete. Plastol 3610 N shows improved finishing characteristics when compared to other commonly used admixtures. Plastol 610 N doesn't contain Calcium Chloride.

PRIMARY APPLICATIONS

- Cast in Place
- Ready mix Concrete
- Flowable Concrete
- Concrete mixtures utilizing Fly Ash, Slag or other natural pozzolans
- SCC and Low fines Concrete

FEATURES/BENEFITS

Plastic Concrete

- Improves finishability
- Improves workability
- Reduces water requirement
- Improves setting time
- Excellent slump retention

Hardened Concrete

- Increases all strength
- Reduces permeability
- Increases durability
- Improves finished appearance
- Achieve high early strength

TECHNICAL INFORMATION

Performance Data:

PROPERTY	VALUE
Physical State	Straw yellow to light brown color liquid
Base Material	Polycarboxylate
Specific Gravity	1.08 ± 0.02 @ 27° C
pH	Minimum 6
Chloride Content	< 0.2 %

Compatible with all cement types like OPC, OPC+Fly ash, PSC etc.,

PACKAGING / YIELD

PLASTOL 3610 N is packaged in 220 Kg HDPE Barrel.

SHELF LIFE

1 Year in original, unopened container.

SPECIFICATIONS/COMPLIANCES

Confirms the requirements of

- IS 9103/2007
- ASTM C 494, Type G
- AASHTO M 194

DIRECTIONS FOR USE

- Normal dosage range is 200 ml - 700 ml / 50 kg of cement.
- However the optimum dosage is determined by site trials.
- Plastol 3610 N should be added to initial batch water of the concrete mixture.
- Do not dispense on to dry cement.
- Over dosing leads to retardation of setting times of concrete, Mix may segregate and bleeding of concrete.

PRECAUTIONS/LIMITATIONS

- Care should be taken to maintain PLASTOL 3610 N above freezing; however, freezing and subsequent thawing will not harm the material if thoroughly agitated. Never agitate with air or an air lance.
- In all cases, refer the Safety Data Sheet before use.